



Altro Whiterock Satins™




Linen | 41
LRV 83



Cescio | 53
LRV 71




Echo | 208
LRV 43




Oyster | 32
LRV 70




Fawn | 206
LRV 41




Ice | 44
LRV 80



Urban | 210
LRV 28




Seafoam | 43
LRV 81




Citron | 56
LRV 80




Fenland | 219
LRV 13



Malva | 57
LRV 68




Clarity | 207
LRV 64




Mint | 203
LRV 62



Daybreak | 222
LRV 69



Sorbet | 216
LRV 59



Zandra | 217
LRV 24



Flint | 201
LRV 32



Promenade | 212
LRV 32




Glow | 215
LRV 50




Scarlett | 221
LRV 13



Viola | 214
LRV 13



Ozone | 211
LRV 10




Vibrance | 213
LRV 22




Olea | 218
LRV 28



Bergamot | 220
LRV 26



Dakota | 209
LRV 6



Orchard | 223
LRV 50



Typical applications / Typische Anwendungsbereiche / Zonas de instalación recomendadas / Type d'applications

Bathrooms, showers and changing rooms. Operating theatres and wards. Splashbacks. Cooking and food preparation areas. Serveries. Kitchens open to public view.

Küchen, Essenstheken, Lebensmittelzubereitung. Showküchen. Klinische-, Pflege- und Spa-Bereiche: Badezimmer, Duschen und Umkleiden. Operationssäle und Stationen.

Baños, duchas y zonas de vestuarios. Quirófanos y pasillo. Salpicaderos. Zonas de cocinado y preparación de alimentos. Minibares. Cocinas abiertas al público.

Salles de bain, douches et vestiaires. Blocs opératoires et salles d'hôpitaux. Crédences de cuisine.

Technical information / Technische Informationen / Información técnica / Information technique

Surface finish	Oberfläche	Acabado de la superficie	Finition	Satin, Satin, Satinado, Satin	
Thickness	Gesamtdicke	Espesor	Epaisseur	2.5 mm	
Size	Größe	Dimensiones	Dimension	2500 mm x 1220 mm 3000 mm x 1220 mm	
Weight	Flächengewicht	Peso	Poids	3600 g/m²	
Maximum service temperature	Max. Betriebstemperatur	Temperatura máxima de uso	Température maximale supportée	60°C	
E-modulus of elasticity	Bruchfestigkeit	Módulos de elasticidad	Module d'élasticité	ISO 527	2950 MPa
Notched Impact resistance	Kratz- und Kerbzähigkeit (Charpy)	Resistencia al impacto	Résistance à l'impact	ISO 179/1ea	9.5 KJ/m²
Flexural strength	Biegefestigkeit	Resistencia a la flexión	Résistance à la flexion	ISO 178	70 MPa
Tensile strength	Zugfestigkeit	Resistencia a la tensión	Résistance à la traction	ISO 527	52 MPa
Shore D hardness	Shore D-Härte	Dureza (Shore D)	Dureté Shore D	ISO 868	76
Thermal conductivity- 'K Value'	Wärmeleitung	Conductividad térmica	Conductivité thermique	EN 12524	0.17 W/mK
Water absorption	Wasserabsorption	Absorción de agua	Imperméabilité	ISO 62	≤ 0.1%
Moisture vapour transmission rate (MVTR)	Wasserdampfdurchlässigkeitsrate (MVTR)	Rango de transmisión de humedad de vapor (MVTR)	Taux de transmission de vapeur d'eau	ASTM E96	≤ 0.12 g/m²/24h
Fire performance	Brandverhalten	Resistencia al fuego	Réaction au feu	EN 13501-1	B- s3, d0
				BS 476 pt 6	Class 0, Klasse 0, Clase 0, Classe 0
				BS 476 pt 7	Class 1, Klasse 1, Clase 1, Classe 1



Altro Limited a company certified by SGS to ISO 9001 and ISO 14001.



2812
EN 15102



1121
EN 15102

