



**Designed for possibilities.
Made for people.**

Altro Whiterock wall designs

Altro Whiterock wall designs



Soft Woodgrain | 9901
LRV 52



Warm Woodgrain | 9904
LRV 38



Rich Woodgrain | 9902
LRV 14

Order No.	Sheet size	Example
Bestell-Nr.	Abmessungen	Beispiel
Número de pedido	Dimensiones	Ejemplo
Commande No.	Format	Exemple
WDS25	2500 x 1220 mm	Brushed Steel: WDS25 / 9911
WDS30	3000 x 1220 mm	Brushed Steel: WDS30 / 9911



Winter Weave | 9909
LRV 58



Autumn Weave | 9910
LRV 43



Summer Weave | 9908
LRV 36

LRV = light reflectance value LRV = Lichtreflexionsgrad LRV = Valor de reflectancia de la Luz LRV = IRL : Indice de Réflexion Lumineuse

Light reflectance values measured in accordance with BS 8493:2008.

Lichtreflexionsgrad (LRV) gemäß BS 8493: 2008.

Los valores de reflectancia de la luz se miden de acuerdo con BS 8493:2008.

Les valeurs de l'indice de Réflexion Lumineuse sont mesurées conformément au BS 8493 :2008.



White Mineral | 9905
LRV 61



Cool Mineral | 9906
LRV 48



Urban Mineral | 9907
LRV 28

Exact material match with samples cannot be guaranteed.
Eine exakte Übereinstimmung des Materials mit Mustern kann nicht garantiert werden.
Las muestras no pueden garantizar un color exacto.
Les échantillons ne peuvent garantir le coloris exact.



Brushed Steel | 9911
LRV 54

Coordinating and contrasting trims available.
Farblich passende und kontrastierende Profile verfügbar.
Molduras en tonos que contrastan o combinan.
Profils de coordination et de contraste disponibles.



Antique Copper | 9912
LRV 9





Typical applications / Typische Anwendungsbereiche / Zonas de instalación recomendadas / Type d'applications

This product is for areas where visual texture is desired, rather than the block colour offered by Altro Whiterock Satins™ and Altro Whiterock Chameleon™.

Ideal for: reception and circulation and cafes within healthcare, education and retail.

Front of house areas in hotels, restaurants and bars. Bathrooms, showers and changing rooms.

Este producto resulta idóneo para las áreas donde se desea crear una textura visual en lugar de color uniforme en bloque propio de Altro Whiterock Satins y Altro Whiterock Chameleon.

Ideal para: baños, duchas y vestuarios, áreas de recepción, zonas de paso así como zonas de café, dentro de los sectores siguientes: sanidad / sector hospitalario, educación y venta al por menor.

Dieses Produkt ist geeignet für Bereiche, in denen eine visuelle Struktur erwünscht ist statt einer Blockfarbe, wie sie Altro Satins und Altro Whiterock Chameleon anbietet.

Ideal für Badezimmer, Duschen und Umkleiden, Empfangs- und Verkehrsbereiche und Cafés im Gesundheits- und Bildungswesen sowie im Einzelhandel.

Ce produit est destiné aux projets d'architecture d'intérieur privilégiant un aspect visuel texturé différent des coloris unis disponibles dans les gammes Altro Whiterock Satins et Altro Whiterock Chameleon.

Idéal pour : les salles de bains, les douches et les vestiaires, les espaces d'accueil, les circulations et les cafés dans le secteur de la santé, l'enseignement et les commerces.

Technical information / Technische Informationen / Información técnica / Information technique

Surface finish	Oberfläche	Acabado de la superficie	Finition	Satin, Satin, Satinado, Satin	
Thickness	Gesamtstärke	Espesor	Epaisseur	2.5 mm	
Size	Format	Dimensiones	Dimension	2500 mm x 1220 mm	
				3000 mm x 1220 mm	
Weight	Flächengewicht	Peso	Poids	3600 g/m²	
Maximum service temperature	Max. Betriebstemperatur	Temperatura máxima de uso	Température maximale supportée	60°C	
E-modulus of elasticity	Bruchfestigkeit	Módulos de elasticidad	Module d'élasticité	ISO 527	2950 MPa
Notched Impact resistance	Kratz- und Kerbzähigkeit (Charpy)	Resistencia al impacto	Résistance à l'impact	ISO 179/1ea	9.5 KJ/m²
Flexural strength	Biegefestigkeit	Resistencia a la flexión	Résistance à la flexion	ISO 178	70 MPa
Tensile strength	Zugfestigkeit	Resistencia a la tensión	Résistance à la traction	ISO 527	52 MPa
Shore D hardness	Shore D-Härte	Dureza (Shore D)	Dureté Shore D	ISO 868	76
Thermal conductivity- 'K Value'	Wärmeleitung	Conductividad térmica	Conductivité thermique	EN 12524	0.17 W/mK
Water absorption	Wasserabsorption	Absorción de agua	Imperméabilité	ISO 62	≤ 0.1%
Moisture vapour transmission rate (MVTR)	Wasserdampfdurchlässigkeitsrate (MVTR)	Rango de transmisión de humedad de vapor (MVTR)	Taux de transmission de vapeur d'eau	ASTM E96	≤ 0.12 g/m²/24h
Fire performance	Brandverhalten	Resistencia al fuego	Réaction au feu	EN 13501-1	B- s3, d0
				BS 476 pt 6	Class 0, Klasse 0, Clase 0, Classe 0
				BS 476 pt 7	Class 1, Klasse 1, Clase 1, Classe 1