


Altro Whiterock White™

**Order No.**

Bestell-Nr.

Número de pedido

Commande No.

W103**W104****Sheet size**

Abmessungen

Dimensiones

Format

2500 x 1220 mm

3000 x 1220 mm


LRV 89

For more colourful solutions / Mehr Möglichkeiten für Ihre Projekte
Añade color a tus proyectos / Pour un choix plus large de couleurs

Altro Whiterock Satins™


Available in 27 shades / in 27 Farben verfügbar

Disponible en 27 tonalidades / Disponible en 27 couleurs

**Altro Whiterock Chameleon™**

Available in 16 shades / in 16 Farben verfügbar

Disponible en 16 tonalidades / Disponible en 16 couleurs



Typical Applications / Typische Anwendungsbereiche / Zonas de instalación recomendadas / Type d'applications

Kitchens: cold store, cook, chill, food prep. Clinical areas. Clean rooms. Laundries. Mortuaries. Bathrooms. Showers and changing areas. Restaurants de comida rápida. Lavanderías. Funerarias. Cuisine : zones froides ou de cuisson, zones réfrigérées ou de préparation alimentaire. Cliniques. Salles blanches. Laveries. Chambres Mortuaires. Küchen: Kühlhäuser, Lebensmittelzubereitung. Klinische Bereiche. Reinräume.

Technical information / Technische Informationen / Información técnica / Information technique

Surface finish	Oberfläche	Acabado de la superficie	Finition	Satin, Satin, Satinado, Satin	
Thickness	Gesamtstärke	Espesor	Epaisseur	2.5 mm	
Size	Format	Dimensiones	Dimension	2500 mm x 1220 mm 3000 mm x 1220 mm	
Weight	Flächengewicht	Peso	Poids	3600 g/m²	
Maximum service temperature	Max. Betriebstemperatur	Temperatura máxima de uso	Température maximale supportée	60°C	
E-modulus of elasticity	Bruchfestigkeit	Módulos de elasticidad	Module d'élasticité	ISO 527	2950 MPa
Notched Impact resistance	Kratz- und Kerbzähigkeit (Charpy)	Resistencia al impacto	Résistance à l'impact	ISO 179/1ea	9.5 KJ/m²
Flexural strength	Biegefestigkeit	Resistencia a la flexión	Résistance à la flexion	ISO 178	70 MPa
Tensile strength	Zugfestigkeit	Resistencia a la tensión	Résistance à la traction	ISO 527	52 MPa
Shore D hardness	Shore D-Härte	Dureza (Shore D)	Dureté Shore D	ISO 868	76
Thermal conductivity- 'K Value'	Wärmeleitung	Conductividad térmica	Conductivité thermique	EN 12524	0.17 W/mK
Water absorption	Wasserabsorption	Absorción de agua	Imperméabilité	ISO 62	≤ 0.1 %
Moisture vapour transmission rate (MVTR)	Wasserdampfdurchlässigkeitsrate (MVTR)	Rango de transmisión de humedad de vapor (MVTR)	Taux de transmission de vapeur d'eau	ASTM E96	≤ 0.12 g/m²/24h
Fire performance	Brandverhalten	Resistencia al fuego	Réaction au feu	EN 13501-1	B- s3, d0
				BS 476 pt 6	Class 0, Klasse 0, Clase 0, Classe 0
				BS 476 pt 7	Class 1, Klasse 1, Clase 1, Classe 1



Altro Limited a company certified by SGS to ISO 9001 and ISO 14001.



Altro Whiterock White | Altro Limited, Works Road, Letchworth Garden City, Hertfordshire, SG6 1NW, UK EN 15102:2007+A1:2011 | Dep-No.W1001
Reaction to fire: B s3 d0
Wall covering for use in a building

